



SKANDIA

5000 N. Highway 251 * Davis Junction, IL 61020
 815.393.4600 * 815.393.3501 (fax)
 www.SkandiaInc.com

60 DEGREE BUNSEN BURNER TEST FOR WIRE 14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)	Skandia, Inc. WO # 248533-12 Client PO 16978-N
--	---

Pic Wire & Cable N63 W22619 Main St. P.O. Box 330 Sussex WI 53089-0330	Doc ID: 60DEG-269740 Test Plan # Rev
---	--

AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION

Make: Stock	Model: N/A	Serial: N/A	Tail: N/A
-------------	------------	-------------	-----------

Conditioning Room Data: Date In: 11/15/2012 Time In: 16:20 Date Out: 11/19/2012 Time Out: 13:28

SPECIMEN MATERIALS

Part No: **E13426**
 PIC Wire & Cable: USB Cable, White, Gauge 26, Ref. # 13405500001

Set	Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drip Flame Time (seconds)
1	30	0.0	0.9	0.0
2	30	0.0	1.0	0.0
3	30	0.0	1.0	0.0
Average:		0.0	1.0	0.0

*60 Degree Bunsen Burner Test (30 seconds): Average Flame Time may not exceed 30 seconds.
 Average Burn Length may not exceed 3 inches. Average Drip Flame Time may not exceed 3 seconds after falling.*

Comments:

Passed Failed

CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, revised as of January 1, 2004 and the Aircraft Materials Fire test Handbook dated April, 2000.

Jennifer Paluzzi -FAA DER WITNESS	11/19/2012 DATE
--------------------------------------	--------------------