



60 DEGREE BUNSEN BURNER TEST FOR WIRE 14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)		Skandia, Inc. WO # 316345-16 Client PO 20475-N		
Pic Wire & Cable N53 W24747 S. Corporate Circle Sussex WI 53089 USA		Doc ID: 60DEG-362361 Test Plan # Rev Project # Technician Olivia Mosqueda		
AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION				
Make: Stock	Model: N/A	Serial: N/A	Tail: N/A	
Conditioning Room Data: Date In: 11/09/2016 Time In: 09:40		Date Out: 11/10/2016 Time Out: 16:07		
SPECIMEN MATERIALS				
Part No: E20224 Pic Wire & Cable: Wire, White, .141 Nom. Diameter Lot No 241500				
Set	Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drip Flame Time (seconds)
1	30	0.0	1.8	0.0
2	30	0.0	1.7	0.0
3	30	0.0	1.8	0.0
Average:		0.0	1.8	0.0
<i>60 Degree Bunsen Burner Test (30 seconds): Average Flame Time may not exceed 30 seconds. Average Burn Length may not exceed 3 inches. Average Drip Flame Time may not exceed 3 seconds after falling.</i>				
Comments:				
<input checked="" type="checkbox"/> Passed <input type="checkbox"/> Failed				
CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, or the Aircraft Materials Fire test handbook. Not FAA approved unless an 8110-3 has been issued.				
DER Jane Biberstein		11/10/2016		
WITNESS		DATE		