

## Making Aircraft Quieter, Safer and More Comfortable. 5000 North Highway 251, Davis Junction, IL 61020 I 800 945 7135 I www.skandiainc.com

60 DEGREE BUNSEN BURNER TEST FOR WIRE				Skandia, Inc WO# 356063-19		
14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)				Client PO 22696-00		
N53 W	re & Cable /24747 S. Corporate Circle x WI 53089 USA			Doc ID Test Plan # Rev	60DEG-428820	
				Project # Technician	Sammy Losoya	
AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION						
Make: Stock Mode		odel: Se	el: Serial: N/A Tail:			
Conditioning Room Data: Date In: 04/08/2019 Time In: 8:30 AM Date Out: 04/09/2019 Time Out: 1:32 PM						
		SPECIMEN MATER	RIALS			
Test Set	Flame Application	Flame Time (seconds)	Pura Lon	oth (inches)	Dis El Timo	
rost oct	(seconds)	Flame Time (seconds)	Burn Len	igth (inches)	Drip Flame Time (seconds)	
1	30	0.0		1.6	0.0	
2	30	0.0		1.8	0.0	
3	30	0.0	1.6		0.0	
Average:		0.0	1.7		0.0	
Average Comments:	60 Degree Bunsen Burner Burn Length may not exce	Test (30 Seconds): Average F ed 3 inches. Average Drip Fla	Flame time si me Time ma	hall not exceed S	d 30 seconds. 3 seconds after falling.	
CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, or the Aircraft Materials Fire test nandbook. Not FAA approved unless an 8110-3 has been issued.  DER Jane Biberstein    V   Passed   Failed   Fa						
	WITNESS	MY HUNN	DATE			
			DAIL			