

Making Aircraft Quieter, Safer and More Comfortable.
5000 North Highway 251, Davis Junction, IL 61020 I 800 945 7135 I www.skandiainc.com

60 DEGREE BUNSEN BURNER TEST FOR WIRE 14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)				Skandia, Inc. WO # 313802-16 Client PO 20357-N			
Pic Wire & Cable N53 W24747 S. Corporate Circle				Doc ID: 60DEG-358508 Test Plan # Rev			
Sussex WI 53089 USA				Project # Technician Olivia Mosqueda			
AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION							
Make: Stock		Model:N/A Seria		A Tail: N/A		Tail: N/A	
Conditioning Room Data: Date In: 09/16/2016 Time In: 10:05 Date Out: 09/19/2016 Time Out: 12:31							
SPECIMEN MATERIALS							
Part No: L8620TX							
Pic Wire & Cable: Wire, White, .173 nom. Diameter							
Lot No 150329							
Set	Flame Application (seconds)	Flame Time		ength	Drip Flame Time		
	(seconds)	(seconds)	(inches)		(seconds)		
1	30	0.0	1.5		0.0		
2	30	0.0	1.6		0.0		
3	30	0.0	1.6		0.0		
	Average:	0.0		1.6		0.0	
60 Degree Bunsen Burner Test (30 seconds): Average Flame Time may not exceed 30 seconds.  Average Burn Length may not exceed 3 inches. Average Drip Flame Time may not exceed 3 seconds after falling.							
Comments:							
CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, or the Aircraft Materials Fire test handbook. Not FAA approved unless an 8110-3 has been issued.							
DER Jane Biberstein 09/19/2016						09/19/2016	
	WITNESS						