



60 DEGREE BUNSEN BURNER TEST FOR WIRE 14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)	Skandia, Inc. WO # 305030-16 Client PO 19992-N
--	---

Pic Wire & Cable N53 W24747 S. Corporate Circle Sussex WI 53089 USA	Doc ID: 60DEG-346070 Test Plan # Rev Project # Technician Jason Manning
---	---

AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION

Make: Stock	Model:N/A	Serial: N/A	Tail: N/A
-------------	-----------	-------------	-----------

Conditioning Room Data: Date In: 03/16/2016 Time In: 09:55 Date Out: 03/17/2016 Time Out: 13:38

SPECIMEN MATERIALS

Part No: **S65161-A**
 Pic Wire & Cable: Wire, White, .195 nom. OD

Lot No 3329

Set	Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drip Flame Time (seconds)
1	30	0.0	1.3	0.0
2	30	0.0	1.2	0.0
3	30	0.0	1.3	0.0
Average:		0.0	1.3	0.0

*60 Degree Bunsen Burner Test (30 seconds): Average Flame Time may not exceed 30 seconds.
 Average Burn Length may not exceed 3 inches. Average Drip Flame Time may not exceed 3 seconds after falling.*

Comments:

Passed **Failed**

CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, or the Aircraft Materials Fire test handbook. Not FAA approved unless an 8110-3 has been issued.

DER Jane Biberstein		03/17/2016
WITNESS		DATE