

Making Aircraft Quieter, Safer and More Comfortable. 5000 North Highway 251, Davis Junction, IL 61020 I 800 945 7135 I www.skandiainc.com

60 DEGREE BUNSEN BURNER TEST FOR WIRE				Skandia, Inc WO# 356063-19		
14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3))	Client PO 22696-00		
Pic Wire & Cable				Doc ID	60DEG-428822	
N53 W24747 S. Corporate Circle				Test Plan #		
Sussex WI 53089 USA				Rev		
				Project #		
				Technician	Sammy Losoya	
AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION						
Make: Stock Mode		: Serial: N/A Tail:				
Conditioning Room Data: Date In: 04/08/2019 Time In: 8:30 AM Date Out: 04/09/2019 Time Out: 1:48 PM						
		SPECIMEN MATER	RIALS			
PIC Wire & Ca	able: Cable, White, Wire Gauç	ge 26				
Test Set	Flame Application (seconds)	Flame Time (seconds)	Burn Leng	gth (inches)	Drip Flame Time (seconds)	
1	30	0.0	2	0	0.0	
2	30	0.0	2	3	0.0	
3	30	0.0	1	.7	0.0	
Average:		0.0	2	.0	0.0	
	60 Degree Bunsen Burner Te Burn Length may not exceed					
Comments:					*	
				X Pas	ssed Failed	
CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, or the Aircraft Materials Fire test handbook. Not FAA approved unless an 8110-3 has been issued.						
DER Jane Biberstein			MA	04/09/2019		
	WITNESS	AN LONG		DATE		