

Making Aircraft Quieter, Safer and More Comfortable. 5000 North Highway 251, Davis Junction, IL 61020 I 800 945 7135 I www.skandiainc.com

60 DEGREE BUNSEN BURNER TEST FOR WIRE				Skandia, Inc WO# 336717-18		
14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)				Client PO 21536N		
Pic Wire & Cable				Doc ID	60DEG-394978	
N53 W24747 S. Corporate Circle				Test Plan #		
Sussex WI 53089 USA				Rev		
				Project #		
				Technician	Olivia Mosqueda	
	AIRCR	AFT OR AIRCRAFT COMPONENT I	DENTIFICATION	DN .		
Make: stock Mod		odel: Se	el: Serial: N/A Ta		l:	
Conditioning Ro	oom Data: Date In: 01/18	/2018 Time In: 10:35 AM	Date Out:	01/19/2018	Time Out: 12:31 PM	
		SPECIMEN MATER	IALS			
	3-2624 orp: Cable, White					
Test Set	Flame Application (seconds)	Flame Time (seconds)	Burn Le	ngth (inches)	Drip Flame Time (seconds)	
1	30	0.0		1.0	0.0	
2	30	0.0		1.0	0.0	
3	30	0.0		1.0	0.0	
Average:		0.0	1.0		0.0	
	-	Test (30 Seconds): Average I ed 3 inches. Average Drip Fla				
CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, or the Aircraft Materials Fire test handbook. Not FAA approved unless an 8110-3 has been issued. O1/19/2018						
DER Jane Biberstein				/		
WITNESS				DATE		
	17.	N .				