



60 DEGREE BUNSEN BURNER TEST FOR WIRE 14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)	Skandia, Inc. WO # 298212-15 Client PO 19605-N
--	---

Pic Wire & Cable N53 W24747 S. Corporate Circle Sussex WI 53089 USA	Doc ID: 60DEG-336724 Test Plan # Rev Project # Technician Mike Thompson
---	---

AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION

Make: Stock	Model:N/A	Serial: N/A	Tail: N/A
-------------	-----------	-------------	-----------

Conditioning Room Data: Date In: 10/26/2015 Time In: 10:15 Date Out: 10/27/2015 Time Out: 13:21

SPECIMEN MATERIALS

Part No: **E51424**
 Pic Wire & Cable: Wire, Coax, White, 24 Awg

 Lot No 000148501001004

Set	Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drip Flame Time (seconds)
1	30	0.0	1.4	0.0
2	30	0.0	1.4	0.0
3	30	0.0	1.3	0.0
Average:		0.0	1.4	0.0

*60 Degree Bunsen Burner Test (30 seconds): Average Flame Time may not exceed 30 seconds.
 Average Burn Length may not exceed 3 inches. Average Drip Flame Time may not exceed 3 seconds after falling.*

Comments:

Passed **Failed**

CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, or the Aircraft Materials Fire test handbook. Not FAA approved unless an 8110-3 has been issued.

Jane Biberstein -FAA DER WITNESS	 10/27/2015 DATE
--	-------------------------------