



<b>60 DEGREE BUNSEN BURNER TEST FOR WIRE</b> 14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)	Skandia, Inc. WO # 300294-15 Client PO 19720-N
--	---

Pic Wire & Cable N53 W24747 S. Corporate Circle  Sussex WI 53089 USA	Doc ID: 60DEG-339597 Test Plan # Rev  Project # Technician Joy Kortte
---	--

**AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION**

Make: Stock	Model: N/A	Serial: N/A	Tail: N/A
-------------	------------	-------------	-----------

Conditioning Room Data:    Date In: 12/08/2015    Time In: 09:15                      Date Out: 12/09/2015    Time Out: 10:40

**SPECIMEN MATERIALS**

Part No: **D620222**  
 Pic Wire & Cable: Wire, White, .160 nom.  
  
  
 Lot No    153896

Set	Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drip Flame Time (seconds)
1	30	0.0	1.9	0.0
2	30	0.0	1.8	0.0
3	30	0.0	1.7	0.0
<b>Average:</b>		0.0	1.8	0.0

*60 Degree Bunsen Burner Test (30 seconds): Average Flame Time may not exceed 30 seconds.  
 Average Burn Length may not exceed 3 inches. Average Drip Flame Time may not exceed 3 seconds after falling.*

Comments: This data sheet supersedes previous data sheet dated 12/09/2015 to correct part number.

**Passed**     **Failed**

CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, or the Aircraft Materials Fire test handbook. Not FAA approved unless an 8110-3 has been issued.

Jennifer Paluzzi -FAA DER <b>WITNESS</b>	 01/08/2016 <b>DATE</b>
---	-------------------------------