



SKANDIA

5000 N. Highway 251 ■ Davis Junction, IL 61020
815.393.4600 ■ 800.945.7135
www.SkandiaInc.com

Client: Pic Wire & Cable
N63 W22619 Main St.
P.O. Box 330
Sussex WI 53089-0330

WO #: 180885-08
Date: 04/30/08
Test Plan #:
PO #:

Aircraft:
Stock

S/N: NA
Tail #: N/A
Test ID #: 60DEG-1369

60 Degree Bunsen Burner Test For Wire

14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)

Conditioning Room: Time In: 04/29/08 09:00 AM Time Out: 04/30/08 09:16 AM

Specimen: PIC Wire & Cable: Wire, DVI 50824, White, AWG 24, Ref # bar code 000013551000001

Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drip Flame Time (Seconds)
30	0.0	1.3	0
30	0.0	1.2	0
30	0.0	0.8	0
Average:	0.0	1.1	0

Comments:

60 Degree Bunsen Burner Test (30 sec.): Average Flame Time may not exceed 30 sec. Average Burn Length may not exceed 3". Average Drip Flame Time may not exceed 3 sec. after falling.

Passed: Failed:

Signed: Carin Demus
Carin Demus