



# SKANDIA

5000 N. Highway 251 ■ Davis Junction, IL 61020  
815.393.4600 ■ 800.945.7135  
www.SkandiaInc.com

Client: Pic Wire & Cable  
N63 W22619 Main St.  
P.O. Box 330  
Sussex WI 53089-0330

WO #: 184083-08  
Date: 06/30/08  
Test Plan #:  
PO #: Verbal

Aircraft:  
Stock

S/N: NA  
Tail #: N/A  
Test ID #: 60DEG-1462

### 60 Degree Bunsen Burner Test For Wire

14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)

Conditioning Room: Time In: 06/27/08 09:00 AM Time Out: 06/30/08 02:10 PM

Specimen: Pic Wire & Cable: Wires, E10222, White/Blue, 22 AWG, Lot #0000123160

Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drip Flame Time (Seconds)
30	0.0	0.8	0
30	0.0	1.3	0
30	0.0	1.0	0
Average:	0.0	1.0	0

#### Comments:

60 Degree Bunsen Burner Test (30 sec.): Average Flame Time may not exceed 30 sec. Average Burn Length may not exceed 3". Average Drip Flame Time may not exceed 3 sec. after falling.

Passed:  Failed:

Signed: Carin Demus  
Carin Demus