



SKANDIA

5000 N. Highway 251 ■ Davis Junction, IL 61020
815.393.4600 ■ 800.945.7135
www.SkandiaInc.com

Client: Pic Wire & Cable
N63 W22619 Main St.
P.O. Box 330
Sussex WI 53089-0330

WO #: 161221-07
Date: 05/10/07
Test Plan #:
PO #: Verbal

Aircraft:
Stock

S/N:
NA

60 Degree Bunsen Burner Test For Wire

14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)

Conditioning Room: Time In: 05/07/07

Time Out: 05/10/07

Specimen: Pic Wire & Cable: Wire, E30824, 24AWG, Lot #13471

Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drip Flame Time (Seconds)
30	0.0	0.6	0 No Drips
30	0.0	0.3	0 No Drips
30	0.0	0.7	0 No Drips
Average:	0.0	0.5	0 No Drips

Comments:

60 Degree Bunsen Burner Test (30 sec.): Average Flame Time may not exceed 30 sec. Average Burn Length may not exceed 3". Average Drip Flame Time may not exceed 3 sec. after falling.

Passed: Failed:

Signed: 
Carin Demus