



Making Aircraft Quieter, Safer and More Comfortable.  
 5000 North Highway 251, Davis Junction, IL 61020 | 800 945 7135 | www.skandiainc.com

<b>60 DEGREE BUNSEN BURNER TEST FOR WIRE</b> 14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)		Skandia, Inc. WO # 284384-15 Client PO 18896-N
Pic Wire & Cable N53 W24747 S. Corporate Circle  Sussex WI 53089 USA		Doc ID: 60DEG-316864 Test Plan # Rev  Project # Technician Rickey Ryerson

AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION			
Make: Stock	Model: N/A	Serial: N/A	Tail: N/A
Conditioning Room Data:	Date In: 01/12/2015	Time In: 09:52	Date Out: 01/13/2015 Time Out: 15:06

SPECIMEN MATERIALS	
Part No: <b>S44193</b>	Pic Wire & Cable: Wire, Coax, Clear
Lot No	000136288

Set	Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drip Flame Time (seconds)
1	30	0.0	1.2	0.0
2	30	0.0	1.2	0.0
3	30	0.0	1.1	0.0
<b>Average:</b>		0.0	1.2	0.0

*60 Degree Bunsen Burner Test (30 seconds): Average Flame Time may not exceed 30 seconds. Average Burn Length may not exceed 3 inches. Average Drip Flame Time may not exceed 3 seconds after falling.*

Comments:

Passed  Failed

CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, revised as of January 1, 2004 and the Aircraft Materials Fire test Handbook dated April, 2000.

Rickey Ryerson  
 WITNESS

01/13/2015  
 DATE