



60 DEGREE BUNSEN BURNER TEST FOR WIRE 14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)	Skandia, Inc WO# 409490 Client PO 26184N
--	---

Pic Wire & Cable N53 W24747 S. Corporate Circle Sussex WI 53089 USA	Doc ID 60DEG-500668 Test Plan # Rev Project # Technician Rickey Ryerson
---	---

AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION

Make: Stock	Model:	Serial: N/A	Tail:
-------------	--------	-------------	-------

Conditioning Room Data: Date In: 09/26/2023 Time In: 2:40 PM Date Out: 09/27/2023 Time Out: 3:27 PM

SPECIMEN MATERIALS

Part No: **HDMI1926-HS**
 PIC Wire & Cable: Cable, HDMI, White, 26, Ref # 010001

Lot No: 000082223

Test Set	Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drip Flame Time (seconds)
1	30	0.0	1.2	0.0
2	30	0.0	1.1	0.0
3	30	0.0	1.1	0.0
Average:		0.0	1.1	0.0

*60 Degree Bunsen Burner Test (30 Seconds): Average Flame time shall not exceed 30 seconds.
 Average Burn Length may not exceed 3 inches. Average Drip Flame Time may not exceed 3 seconds after falling.*

Comments:

Passed **Failed**

CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, or the Aircraft Materials Fire test handbook. Not FAA approved unless an 8110-3 has been issued.

09/27/2023

WITNESS **DATE**

Test results relate only to the items tested. Results apply to the sample as received (as applicable).
 Uncertainty is not taken into account in the statement of conformity in relation to the test results.