



# SKANDIA

5000 N. Highway 251 ■ Davis Junction, IL 61020  
 815.393.4600 ■ 815.393.3501 (fax)  
 www.SkandiaInc.com

<b>60 DEGREE BUNSEN BURNER TEST FOR WIRE</b> 14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)		Skandia, Inc. WO # 208203-10 Client PO Verbal
Pic Wire & Cable N63 W22619 Main St. P.O. Box 330  Sussex WI 53089-0330		Doc ID: 60DEG-216558 Test Plan # Rev

AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION			
Make: Stock	Model: N/A	Serial: N/A	Tail: N/A
Conditioning Room Data:	Date In: 01/14/2010	Time In: 10:45	Date Out: 01/15/2010 Time Out: 10:56

SPECIMEN MATERIALS	
Pic Wire & Cable: Cable, Part #E6A0824, 24 AWG, Lot #117284 p/u 004	


Set	Flame Application (seconds)	Flame Time (seconds)	Burn Length (seconds)	Drip Flame Time (seconds)
1	30	0.0	0.2	0.0
2	30	0.0	0.3	0.0
3	30	0.0	0.2	0.0
<b>Average:</b>		0.0	0.2	0.0

*60 Degree Bunsen Burner Test (30 seconds): Average Flame Time may not exceed 30 seconds. Average Burn Length may not exceed 3 inches. Average Drip Flame Time may not exceed 3 seconds after falling.*

Comments:

**Passed**  **Failed**

CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, revised as of January 1, 2004 and the Aircraft Materials Fire test Handbook dated April, 2000.

Gary K. Palmer - FAA DER <b>WITNESS</b>		01/15/2010 <b>DATE</b>
--	---	---------------------------