



# SKANDIA

5000 N. Highway 251 ■ Davis Junction, IL 61020  
 815.393.4600 ■ 815.393.3501 (fax)  
 www.SkandiaInc.com

<b>60 DEGREE BUNSEN BURNER TEST FOR WIRE</b> 14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)			Skandia, Inc. WO # 248533-12 Client PO 16978-N	
Pic Wire & Cable N63 W22619 Main St. P.O. Box 330  Sussex WI 53089-0330			Doc ID: 60DEG-269712 Test Plan # Rev	
<b>AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION</b>				
Make: Stock		Model: N/A		Tail: N/A
		Serial: N/A		
Conditioning Room Data:    Date In: 11/15/2012    Time In: 16:20    Date Out: 11/19/2012    Time Out: 11:56				
<b>SPECIMEN MATERIALS</b>				
Part No: <b>E51426</b> PIC Wire & Cable: USB Cable, White, Gauge 26, Ref. # 134051000001				
Set	Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drip Flame Time (seconds)
1	30	0.0	1.5	0.0
2	30	0.0	1.6	0.0
3	30	0.0	1.7	0.0
<b>Average:</b>		0.0	1.6	0.0
<i>60 Degree Bunsen Burner Test (30 seconds): Average Flame Time may not exceed 30 seconds. Average Burn Length may not exceed 3 inches. Average Drip Flame Time may not exceed 3 seconds after falling.</i>				
Comments:				
<input checked="" type="checkbox"/> <b>Passed</b> <input type="checkbox"/> <b>Failed</b>				
CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, revised as of January 1, 2004 and the Aircraft Materials Fire test Handbook dated April, 2000.				
Jennifer Paluzzi -FAA DER WITNESS			11/19/2012 DATE	