



Skandia, Inc. WO # 280903-14

Client PO 18674-N

Rev

Technician Rickey Ryerson

AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION

Tail: N/A

Conditioning Room Data: Date In: 10/22/2014 Time In: 10:35 Date Out: 10/23/2014 Time Out: 11:14

SPECIMEN MATERIALS

Pic Wire & Cable: Coax, Clear

Lot No 000138413

Set	Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drip Flame Time (seconds)
1	30	0.0	1.4	0.0
2	30	0.0	1.5	0.0
3	30	0.0	1.3	0.0
Average:		0.0	1.4	0.0

60 Degree Bunsen Burner Test (30 seconds): Average Flame Time may not exceed 30 seconds.

Average Burn Length may not exceed 3 inches. Average Drip Flame Time may not exceed 3 seconds after falling.

Comments:



Passed



Failed

CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, revised as of January 1, 2004 and the Aircraft Materials Fire test Handbook dated April, 2000.

Jane Biberstein -FAA DER

10/23/2014

WITNESS

DATE _____