



Making Aircraft Quieter, Safer and More Comfortable.
5000 North Highway 251, Davis Junction, IL 61020 | 800 945 7135 | www.skandialinc.com

60 DEGREE BUNSEN BURNER TEST FOR WIRE 14 CFR Part 25.869 (a)(4) Amdt 25-113 Appendix F Part I (a)(3)		Skandia, Inc. WO # 278756-14 Client PO 18574-N		
Pic Wire & Cable N53 W24747 S. Corporate Circle Sussex WI 53089 USA		Doc ID: 60DEG-308527 Test Plan # Rev Project # Technician Rickey Ryerson		
AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION				
Make: Stock	Model: N/A	Serial: N/A	Tail: N/A	
Conditioning Room Data:		Date In: 09/09/2014 Time In: 09:50	Date Out: 09/10/2014 Time Out: 10:54	
SPECIMEN MATERIALS				
Part No: S44193 Pic Wire & Cable: Wire, Coax, Clear, 19 AWG, Ref.# 0986 Lot No 000143623				
Set	Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drip Flame Time (seconds)
1	30	0.0	1.3	0.0
2	30	0.0	1.3	0.0
3	30	0.0	1.4	0.0
Average:		0.0	1.3	0.0
60 Degree Bunsen Burner Test (30 seconds): Average Flame Time may not exceed 30 seconds. Average Burn Length may not exceed 3 inches. Average Drip Flame Time may not exceed 3 seconds after falling.				
Comments:				
<div style="text-align: right;"><input checked="" type="checkbox"/> Passed <input type="checkbox"/> Failed</div> <p>CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, revised as of January 1, 2004 and the Aircraft Materials Fire test Handbook dated April, 2000.</p>				
Jennifer Paluzzi -FAA DER		09/10/2014		
WITNESS		DATE		